



(19) **RU** (11) **2 088 620** (13) **C1**
(51) Int. Cl.⁶ **C 09 D 5/03, C 04 B 41/46**

RUSSIAN AGENCY
FOR PATENTS AND TRADEMARKS

(12) **ABSTRACT OF INVENTION**

(21), (22) Application: 93054195/04, 02.12.1993

(46) Date of publication: 27.08.1997

(71) Applicant:
Elesin Mikhail Anatol'evich,
Elesin Anatolij Ivanovich

(72) Inventor: Elesin Mikhail Anatol'evich,
Elesin Anatolij Ivanovich

(73) Proprietor:
Elesin Mikhail Anatol'evich,
Elesin Anatolij Ivanovich

(54) **METHOD OF THE DYING COMPOSITION PREPARING**

(57) Abstract:

FIELD: building materials. SUBSTANCE: method involves the successive mixing calcium hydroxide, white portland cement, powdery elemental sulfur and zinc sulfate in water heated to 90-100 C. These components were taken at the following ratio, wt.-%: calcium hydroxide 30.4; white portland cement 3.4-54.3; powdery elemental sulfur 14.8-19.0, and zinc sulfate 30.9-47.2.

Properties: covering power with the proposed pigment for cement dye, polymercement dye, polyvinyl acetate dye and oily dye - 184; 140; 87 and 78 g/m², respectively. Hardiness - 43; 69; 48 and 90 cycles, respectively. Adhesion to cellular concrete: 1.0; 1.5; 1.0 and 2.4 MPa, respectively, for the proposed dyes. EFFECT: improved method of preparing, enhanced quality and property. 1 tbl

RU 2 088 620 C1

RU 2 088 620 C1